

PATENT APPLICATION  
ATTORNEY DOCKET NO.: 10/786,974Amendments to the Claims

Please amend the claims 1 through 8 as shown and withdraw claims 9-16.

1. (Currently Amended) A silver-colored, tarnish-resistant, corrosion-resistant alloy ~~comprised~~ consisting essentially of:

92.5 to 95% by weight silver, the balance of which is an alloy comprised of:

approximately ~~29.75% ± 5%~~ 24-34% by weight zinc;

approximately ~~62.15% ± 5%~~ 60-74% by weight copper;

approximately ~~1.35% ± 5%~~ 0.5-1.8% by weight silicon; and

approximately ~~6.75% ± 1.25%~~ 0-8% by weight tin.

2. (Currently Amended) A silver-colored, tarnish-resistant, corrosion-resistant alloy consisting essentially of:

92.5 to 95% by weight silver, the balance of which is an alloy ~~comprised~~ consisting essentially of:

approximately ~~19.0% ± 5%~~ 19-29% by weight zinc;

approximately ~~74.8% ± 5%~~ 69.8-79.8% by weight copper; and

approximately ~~1.2% ± 5%~~ .7-1.7% by weight silicon.

3. (Currently Amended) A silver-colored, tarnish-resistant, corrosion-resistant alloy consisting essentially of:

92.5 to 95% by weight silver, the balance of which is an alloy ~~comprised~~ consisting essentially of:

approximately ~~32.60% ± 5%~~ 27.60-37.60% by weight zinc;

approximately ~~64.70% ± 5%~~ 59.7-69.7% by weight copper;

approximately ~~0.60% ± 5%~~ 0.5-1.8% by weight silicon;

approximately ~~0.90% ± 5%~~ 0.90-5% by weight tin; and

approximately ~~1.20% ± 5%~~ 0-1.5% by weight indium.

PATENT APPLICATION  
ATTORNEY DOCKET NO.: 10/786,974

4. (Currently Amended) A silver-colored, tarnish-resistant, corrosion-resistant alloy consisting essentially of:

92.5 to 95% by weight silver, the balance of which is an alloy comprised consisting essentially of:

approximately 29.75% by weight zinc;  
approximately 62.15% by weight copper;  
approximately 1.35% by weight silicon; and  
approximately 6.75% by weight tin.

5. (Currently Amended) A silver-colored, tarnish-resistant, corrosion-resistant jewelry consisting essentially of:

92.5 to 95% by weight silver, the balance of which is an alloy comprised consisting essentially of:

approximately 24.0% by weight zinc;  
approximately 74.8% by weight copper; and  
approximately 1.2% by weight silicon.

6. (Currently Amended) A silver-colored, tarnish-resistant, corrosion-resistant jewelry consisting essentially of:

92.5 to 95% by weight silver, the balance of which is an alloy comprised consisting essentially of:

approximately 32.6% by weight zinc;  
approximately 64.7% by weight copper;  
approximately 0.6% by weight silicon;  
approximately 0.9% by weight tin, and  
approximately 1.2% by weight indium.

7. (Currently Amended) A silver-colored, tarnish-resistant, corrosion-resistant jewelry consisting essentially of:

92.5 to 95% by weight silver, the balance of which is an alloy comprised consisting essentially of:

PATENT APPLICATION  
ATTORNEY DOCKET NO.: 10/786,974

29.75 % by weight zinc;  
62.15% by weight copper;  
1.35% by weight silicon; and  
6.75% by weight tin.

8. A silver-colored, tarnish-resistant, corrosion-resistant jewelry consisting essentially of:  
92.5 to 95% by weight silver, the balance of which is an alloy ~~comprised~~  
consisting essentially of:

32.60 % by weight zinc;  
64.70% by weight copper;  
0.60% by weight silicon;  
0.90% by weight tin; and  
1.20% by weight indium.

9. (Withdrawn).  
10. (Withdrawn).  
11. (Withdrawn).  
12. (Withdrawn).  
13. (Withdrawn).  
14. (Withdrawn).  
15. (Withdrawn).  
16. (Withdrawn).

**This Page is Inserted by IFW Indexing and Scanning  
Operations and is not part of the Official Record**

## **BEST AVAILABLE IMAGES**

Defective images within this document are accurate representations of the original documents submitted by the applicant.

Defects in the images include but are not limited to the items checked:

- ☐ **BLACK BORDERS**
- ☐ **IMAGE CUT OFF AT TOP, BOTTOM OR SIDES**
- ☐ **FADED TEXT OR DRAWING**
- ☐ **BLURRED OR ILLEGIBLE TEXT OR DRAWING**
- ☐ **SKEWED/SLANTED IMAGES**
- ☐ **COLOR OR BLACK AND WHITE PHOTOGRAPHS**
- ☐ **GRAY SCALE DOCUMENTS**
- ☐ **LINES OR MARKS ON ORIGINAL DOCUMENT**
- ☐ **REFERENCE(S) OR EXHIBIT(S) SUBMITTED ARE POOR QUALITY**
- ☐ **OTHER:** \_\_\_\_\_

**IMAGES ARE BEST AVAILABLE COPY.**

**As rescanning these documents will not correct the image problems checked, please do not report these problems to the IFW Image Problem Mailbox.**